

Premium Polyester Plus Durability Characteristics

Product Description:

Camcode's Premium Polyester Plus labels are constructed of a 2.0 mil gloss white polyester face stock, over-laminated with a 1 mil clear polyester, and a .002" high performance permanent pressure sensitive adhesive. This label has good resistance to general purpose and household cleaners, mild acids, oil and water. The adhesive offers high initial tack and good ultimate bond to a wide variety of rough or textured mating surfaces including low surface energy plastics. Expected exterior life is up to two years.

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils [microns])	Film: 2.0 (51) +/- 10% Adhesive: 1.9-2.1 (48-53) +/- 0.1 (3) Liner: 3.1 (79) +/- 10%	ASTM D 3652
Dimensional Stability (%)	No shrinkage observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Chemical Resistance (non printed stock) Household Cleaners: Mild Acid: Oil: Water:	No effect on topcoat or adhesive No effect on topcoat or adhesive No effect on topcoat or adhesive No effect on topcoat or adhesive	ASTM D 896 (Modified for numbers of cycles and cycle time)
Adhesion Properties		
Ultimate peel from various surfaces Stainless Steel: Acrylic: Glass: Polypropylene:	Oz/in (N/m) average 102 (1122) 116 (1276) 101 (1111) 36 (396)	ASTM D 903 (Modified for 72 hour dwell time)
Expected Shear	50 Hours	ASTM D 3654 Method A a. 1 hour dwell b. 1 square inch surface c. 4 pound load
Tack	990 gm/sq. cm.	ASTM D 2979
Expected Exterior Life:	Up to Two Years	
Service Temperature Range:	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature:	50°F (10°C)	
Storage Stability:	Two years when stored at 70°F (21°C) and 50% relative humidity	

*Camcode® is a registered trademark of Horizons Incorporated.

Note: Users must test products in the specific environment anticipated.
Camcode does not warrant performance of its materials in any environment.

CAMCODE®

A Division of Horizons Incorporated.

18531 South Miles Road - Cleveland, Ohio 44128

800.627.3917 - fax: 216.587.4719

customer_service@camcode.com - www.camcode.com